



March 2017

## PELLE CURTENAL PS-ES

### CHARACTERISTIC

Syntan

**Chemical structure** : Syntan and natural polymer

**Apperance** : Solid in powder

**Colour:** : Whitish to yellowish

**pH** : 5,0±0,5

### PROPERTIES AND APPLICATION

- Retanning products based on natural polymers.
- Used to fill and compact the empty and frayed structures of the leather, giving good fullness in flanks and bellies.
- Improve adhesion, elasticity, fibre compaction and buffing.
- Special to get closer structure and short plush. Suitable to avoid grain looseness in the leather to be milled.
- Special for white leathers. All products have good light fastness.
- General dispersing for other retanning products, vegetal extracts, fatliquors or dyes.
- Better response to dyeing, improving the intensity and igualation of dyes.

### ***“TOUCH WITH PELLECURTEX”***

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.



*March 2017*

- Guidance Dosages: In rechroming (% on shaved weight): Add 0,5 – 1,5%.
- In retanning of chrome leather (% on shaved weight): Add 3–6%.
- In retanning of vegetal-chrome leather (% on shaved weight): 2,5–4%.
- In retannage combined with extracts (% on shaved weight): Use 25-30% of extracts weight.

### **STORAGE**

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

### **PACKAGING**

Bulk in 120 kg polyethylene drums.

### ***“TOUCH WITH PELLECURTEX”***

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.