



March 2017

PELLE CURTESOFT PFS-ES

CHARACTERISTIC

Synthetic Fatliquors And Polymers Base

Chemical structure	: Synthetic-waxy polymer
Apperance	: Fluid liquid
Colour	: Yellowish, opalescent
Concentration (%)	: 45±2
pH	: 7,5±0,5

PROPERTIES AND APPLICATION

- Synthetic fatliquors and polymers based on petrol derivates.
- General use fatliqur for all kind of leathers, chrome tanned, vegetal tanned or mixted as well.
- Can be combined with natural fats, improving the stability of general fatliqur mixture.
- Has good leather fixation and excellent penetration, obtaining a fast and uniform distribution of fat through the leather.
- Produce leathers with tight grain and springy feel. Suitable when light

“TOUCH WITH PELLECURTEX”

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.



March 2017

weight leathers are required. Do not reduce the fibers compactation.

- Odourless fatliquors or light-pleasant smell
- Inoxidable and unrancid fatliquors. Good electrolytes stability. Can be used in tanning, retanning, acid and alkaline.
- Especially for white leathers. It improves and can get white leathers with bluish tone and cleaner leathers.
- It improves the bleaching and cleaning of wool leather. Leathers with good tight grain and spring feel are obtained. Garments, gloves, double face, upholstery.
- Guidance Dosages:
 - Pickling bath (% pelt weight): 1-3%
 - Rechoming bath (% on shaved weight): 2-4%
 - General fatliquoring (% on shaved weight): 8-20%

STORAGE

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

PACKAGING

Bulk in 120 kg polyethylene drums.

“TOUCH WITH PELLECURTEX”

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.