



March 2017

## **PELLE CURTESOFT WP-ES**

### **CHARACTERISTIC**

Special Fats

<b>Chemical structure</b>	: Greasing fat polymer
<b>Apperance</b>	: Viscous liquid
<b>Colour:</b>	: White, opalescent
<b>Concentration (%)</b>	: 51±2
<b>pH</b>	: 6,5±0,5
<b>Charge</b>	: Anionic

### **PROPERTIES AND APPLICATION**

- Several special fatliquors range for special applications/articles.
- Having diverse chemical composition.
- Waterproofing fatliquor. Medium level. Recommended for soft articles, like gloves, garments, nappa. It can be used as a single fat.
- Waterproofing Application: It is recommended not to use any surfactant during the process and a make strong neutralisation, not lower than pH 4,8. The maximum effect is achieved after fixation of fat at the end of process with a metallic salt (Cr, Al, Zr).

### ***“TOUCH WITH PELLECURTEX”***

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.



*March 2017*

- It can be used like a touching agent.
- Guidance Dosages: General waterproofing (% on shaved weight):
  - After neutralization prior to retanning: 3-8%
  - In fresh fatliquor bath: 5-10 %
  - As a touching agent together or after fatliquoring: 0,5-2 %.

### **STORAGE**

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

### **PACKAGING**

Bulk in 120 kg polyethylene drums.

### ***“TOUCH WITH PELLECURTEX”***

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.